

# CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 2003

DateRun: 04/10/2003

Experimenters: Jason Marshall

ClientType: Lab

ProjectNumber: Project #1

Substrates: Stainless Steel

PartType: Coupon

Contaminants: Inks

Cleaning Methods: Immersion/Soak

Analytical Methods: Gravimetric

Purpose: Laboratory evaluations of alternative cleaning products

Experimental Procedure: Basic cleaning performance testing was conducted using ASTM G122 as the bases for cleaning.  
Cleaning: 5 min Immersion cleaning with stir-bar agitation @ 120 F  
Rinsing: 1/2 min, manual, in 102 F water (tap)  
Drying: 1 min with heat gun @ 500F  
Contaminant: Cerdec magenta Ink CAS# 119-64-2, 65997-18-4, 1345-24-0, 20667-12-3

## Results:

### Summary:

<b>Substrates:</b>		Stainless Steel				
<b>Contaminants:</b>		Inks				
Company Name:	Product Name:	Conc.:	Efficiency:	Effective:	Observations:	
Florida Chemical Company	Citrus Burst 7	100	34.96	<input type="checkbox"/>		
Florida Chemical Company	D-Limonene	100	52.79	<input type="checkbox"/>		
Brulin Corporation	Nature Sol 100	100	97.90	<input checked="" type="checkbox"/>		
Twin Rivers Technologies	Methyl Ester 1618	100	7.49	<input type="checkbox"/>		
AG Environmental Products	Canola Gold CE110	100	-50.58	<input type="checkbox"/>		
AG Environmental Products	Soy Gold 1000	100	-56.64	<input type="checkbox"/>		
AG Environmental Products	Soy Gold 2000	100	4.97	<input type="checkbox"/>		
AG Environmental Products	Soy Clear 1500	100	96.76	<input checked="" type="checkbox"/>		
United Laboratories International	United 2002 Harvest Gold	100	-31.45	<input type="checkbox"/>		
Vertec BioSolvents	VertecBio Gold Unscented Part Cleaner	100	-59.38	<input type="checkbox"/>		
EcoLink	Vortex	100	39.23	<input type="checkbox"/>		
Finger Lakes Chemical	2-22 D Limonene Industrial Cleaner	100	-54.97	<input type="checkbox"/>		

Conclusion: Many coupons look as if they would be significantly cleaned with just wipe. The ink has been softened, lifted or dissolved to enhance removal. See trial 236A for follow-up.