

# CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 2003  
 DateRun: 04/10/2003  
 Experimenters: Jason Marshall  
 ClientType: Lab  
 ProjectNumber: Project #1  
 Substrates: Stainless Steel  
 PartType: Coupon  
 Contaminants: Inks  
 Cleaning Methods: Immersion/Soak  
 Analytical Methods: Gravimetric  
 Purpose: Laboratory evaluations of alternative cleaning products  
 Experimental Procedure: Basic cleaning performance testing was conducted using ASTM G122 as the bases for cleaning.  
 Cleaning: 5 min Immersion cleaning with stir-bar agitation @ 120 F  
 Rinsing: 1/2 min, manual, in 102 F water (tap)  
 Drying: 1 min with heat gun @ 500F  
 Contaminant: Cerdec magenta Ink CAS# 119-64-2, 65997-18-4, 1345-24-0, 20667-12-3

Results:

Summary:

<b>Substrates:</b>	Stainless Steel				
<b>Contaminants:</b>	Inks				
Company Name:	Product Name:	Conc.:	Efficiency:	Effective:	Observations:
Florida Chemical Company	Citrus Burst 7	100	34.96	<input type="checkbox"/>	
Florida Chemical Company	D-Limonene	100	52.79	<input type="checkbox"/>	
Brulin Corporation	Nature Sol 100	100	97.90	<input checked="" type="checkbox"/>	
Twin Rivers Technologies	Methyl Ester 1618	100	7.49	<input type="checkbox"/>	
AG Environmental Products	Canola Gold CE110	100	-50.58	<input type="checkbox"/>	
AG Environmental Products	Soy Gold 1000	100	-56.64	<input type="checkbox"/>	
AG Environmental Products	Soy Gold 2000	100	4.97	<input type="checkbox"/>	
AG Environmental Products	Soy Clear 1500	100	96.76	<input checked="" type="checkbox"/>	
United Laboratories International	United 2002 Harvest Gold	100	-31.45	<input type="checkbox"/>	
Vertec BioSolvents	VertecBio Gold Unscented Part Cleaner	100	-59.38	<input type="checkbox"/>	
EcoLink	Vortex	100	39.23	<input type="checkbox"/>	
Finger Lakes Chemical	2-22 D Limonene Industrial Cleaner	100	-54.97	<input type="checkbox"/>	

Conclusion: Many coupons look as if they would be significantly cleaned with just wipe. The ink has been softened, lifted or dissolved to enhance removal. See trial 236A for follow-up.