

CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 2003
DateRun: 09/22/2003
Experimenters: Jason Marshall
ClientType: Lab
ProjectNumber: Project #1
Substrates: Steel
PartType: Coupon
Contaminants: Greases
Cleaning Methods: Immersion/Soak
Analytical Methods: Gravimetric
Purpose: Laboratory evaluations of alternative cleaning products

Experimental Procedure: Basic cleaning performance testing was conducted using ASTM G122 as the bases for cleaning. Six products were used at full strength, heated to 120 F on a hot plate. Eighteen preweighed coupons were coated with CRC Industries Multipurpose Super White Grease (64741-96-4, 7620-77-1, 1314-13-2, 57885-77-3, 13463-67-7) and allowed to dry for three days and reweighed. Three coupons were cleaned in each solution for 5 minutes using stir-bar-agitation, rinsed in a tap water bath for 15 seconds at 120 F and dried using air blow off for 30 seconds at 68 F. Coupons were allowed to dry overnight and then reweighed a final time. Efficiencies were calculated.

Note: Bio T Foam Plus was sprayed onto coupons at room temperature and allowed to sit for 5 minutes. The cleaner was then rinsed off.

Results: None of the cleaners removed over 85% of the grease. One product was partially successful, removing just over 70%.

Summary:

Substrates:	Steel					
Contaminants:	Greases					
Company Name:	Product Name:	Conc.:	Efficiency:	Effective:	Observations:	
AW Chesterton	278 Super Solv	100	39.00	<input type="checkbox"/>		
Bio Chem Systems	Bio T Foam Plus	100	8.50	<input type="checkbox"/>		
Eastern Color and Chemical Company	Ecobrite Cleaner AK	100	21.77	<input type="checkbox"/>		
EcoLink	Rip Tide	100	21.12	<input type="checkbox"/>		
EcoLink	VG 151	100	70.09	<input type="checkbox"/>		
Gemtek Products	SC EZ Solv Safety Solvent	100	17.76	<input type="checkbox"/>		

Conclusion: No cleaners were successful in removing the grease within five minutes.