

# CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 2003  
 DateRun: 11/06/2003  
 Experimenters: Dave Hout  
 ClientType: Lab  
 ProjectNumber: Project #1  
 Substrates: Stainless Steel  
 PartType: Coupon  
 Contaminants: Inks  
 Cleaning Methods: Immersion/Soak  
 Analytical Methods: Gravimetric

Purpose: Laboratory evaluations of alternative cleaning products

Experimental Procedure: Basic cleaning performance testing was conducted using ASTM G122 as the bases for cleaning. Four products were heated to 130 F on a hot plate and four others were used at full strength. Twenty-four preweighed coupons were coated with Lithograph Black Ink and allowed to dry for a half an hour and reweighed. Three coupons were cleaned in each solution for 5 minutes using stir-bar-agitation, rinsed in a tap water bath for 15 seconds at 120 F and dried using air blow off for 30 seconds at 68 F. Coupons were allowed to dry for a half an hour and then reweighed a final time. Efficiencies were calculated.

Results:

Summary:

<b>Substrates:</b>	Stainless Steel				
<b>Contaminants:</b>	Inks				
<b>Company Name:</b>	<b>Product Name:</b>	<b>Conc.:</b>	<b>Efficiency:</b>	<b>Effective:</b>	<b>Observations:</b>
Buckeye International	XL 100 Cleaner & Degreaser	5	20.85	<input type="checkbox"/>	
Today & Beyond	Beyond 2003	5	13.22	<input type="checkbox"/>	
US Polychem Corporation	Polychem A 2000 P	5	20.72	<input type="checkbox"/>	
Finger Lakes Chemical	2-22 D Limonene Industrial Cleaner	100	8.53	<input type="checkbox"/>	
ISP Technologies	Ship Shape Resin Cleaner	100	14.25	<input type="checkbox"/>	
Nensco	DT 600 Press Wash	100	3.48	<input type="checkbox"/>	
SOQ Environmental Technology	Ecomate FN	5	13.13	<input type="checkbox"/>	

Conclusion: All products were not effective.