CLEANING LABORATORY EVALUATION SUMMARY

SCL #:	2003
DateRun:	12/29/2003
Experimenters:	Dave Hout
ClientType:	Lab
ProjectNumber:	Project #1
Substrates:	Stainless Steel
PartType:	Coupon
Contaminants:	Lubricating/Lapping Oils
Cleaning Methods:	Immersion/Soak
Analytical Methods:	Gravimetric
Purpose:	Laboratory evaluations of alternative cleaning products
Experimental Procedure:	Basic cleaning performance testing was conducted using ASTM G122 as the bases for cleaning. Two products were heated to 130 F on a hot plate. Six preweighed coupons were coated with Lubricant Houghton MTC-53 and allowed to dry for a half an hour and reweighed. Three coupons were cleaned in each solution for 5 minutes using stir-bar-agitation, rinsed in a tap water bath for 15 seconds at 120 F and dried using air blow off for 30 seconds at 68 F. Coupons were allowed to dry for a half an hour and then reweighed a final time. Effeciencies were calculated.
Results:	
Summary:	

Substrates:	Stainless Steel				
Contaminants:	Lubricating/Lapping Oils				
Company Name:	**Product Name:**	**Conc.:**	**Efficiency:**	**Effective:**	**Observations:**
Valtech Corporation	Valtron SP 2500	5	74.62	☐	
Watson Technical Associates	Watson Formula 9000	5	77.67	☐	

Conclusion: None of the products were effective at removing the contaminant.