

# CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 2004

DateRun: 01/05/2004

Experimenters: Dave Hout

ClientType: Lab

ProjectNumber: Project #1

Substrates: Stainless Steel

PartType: Coupon

Contaminants: Lubricating/Lapping Oils

Cleaning Methods: Immersion/Soak

Analytical Methods: Gravimetric

Purpose: Laboratory evaluations of alternative cleaning products

Experimental Procedure: Basic cleaning performance testing was conducted using ASTM G122 as the bases for cleaning. Two products were heated to 130 F on a hot plate. Six preweighed coupons were coated with Lubricant - LPS Magnum Teflon Lubricant and allowed to dry for a half an hour and reweighed. Three coupons were cleaned in each solution for 5 minutes using stir-bar-agitation, rinsed in a tap water bath for 15 seconds at 120 F and dried using air blow off for 30 seconds at 68 F. Coupons were allowed to dry for a half an hour and then reweighed a final time. Efficiencies were calculated.

## Results:

### Summary:

<b>Substrates:</b>		Stainless Steel			
<b>Contaminants:</b>		Lubricating/Lapping Oils			
<b>Company Name:</b>	<b>Product Name:</b>	<b>Conc.:</b>	<b>Efficiency:</b>	<b>Effective:</b>	<b>Observations:</b>
Valtech Corporation	Valtron SP 2500	5	93.97	<input checked="" type="checkbox"/>	
Watson Technical Associates	Watson Formula 9000	5	95.53	<input checked="" type="checkbox"/>	

Conclusion: Both products were effective at an efficiency rate of >93%