

CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 2004
 DateRun: 01/05/2004
 Experimenters: Dave Hout
 ClientType: Lab
 ProjectNumber: Project #1
 Substrates: Stainless Steel
 PartType: Coupon
 Contaminants: Cutting/Tapping Fluids
 Cleaning Methods: Immersion/Soak
 Analytical Methods: Gravimetric
 Purpose: Laboratory evaluations of alternative cleaning products

Experimental Procedure: Basic cleaning performance testing was conducted using ASTM G122 as the bases for cleaning. Seven products were heated to 130 F on a hot plate and one product was used at full strength. Twenty-four preweighed coupons were coated with Cutting Fluid - Remi Corp Re Lion and allowed to dry for a half an hour and reweighed. Three coupons were cleaned in each solution for 5 minutes using stir-bar-agitation, rinsed in a tap water bath for 15 seconds at 120 F and dried using air blow off for 30 seconds at 68 F. Coupons were allowed to dry for a half an hour and then reweighed a final time. Efficiencies were calculated.

Results:

Summary:

Substrates:	Stainless Steel				
Contaminants:	Cutting/Tapping Fluids				
Company Name:	Product Name:	Conc.:	Efficiency:	Effective:	Observations:
Man Gill Chemical Company	Gillite 1156	100	60.55	<input type="checkbox"/>	
Hubbard Hall Inc	Ram Charger	5	74.94	<input type="checkbox"/>	
Hurri Kleen Corportion	HurriSafe - Hot Immersion Degreaser	5	99.91	<input checked="" type="checkbox"/>	
Heatbath Corporation	MultiKleen LX 1573	5	102.42	<input checked="" type="checkbox"/>	
Chemkleen International Inc.	CT 1 Multipurpose Cleaner	5	101.28	<input checked="" type="checkbox"/>	
Buckeye International	Work Out	5	102.94	<input checked="" type="checkbox"/>	
Delta Omega Technologies Ltd	Attar D(R3)	5	99.97	<input checked="" type="checkbox"/>	
Equinox Products	Natural Solutions	5	102.60	<input checked="" type="checkbox"/>	

Conclusion: 6 out of 8 products were effective at removing the contaminant at an efficiency rate of >99%