

# CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 2004

DateRun: 01/08/2004

Experimenters: Dave Hout

ClientType: Lab

ProjectNumber: Project #1

Substrates: Stainless Steel

PartType: Coupon

Contaminants: Oil

Cleaning Methods: Immersion/Soak

Analytical Methods: Gravimetric

Purpose: Laboratory evaluations of alternative cleaning products

Experimental Procedure: Basic cleaning performance testing was conducted using ASTM G122 as the bases for cleaning. Six products were heated to 130 F on a hot plate and two products were used at full strength. Twenty-four preweighed coupons were coated with Oil - Benecyn B - 5186 and allowed to dry for a half an hour and reweighed. Three coupons were cleaned in each solution for 5 minutes using stir-bar-agitation, rinsed in a tap water bath for 15 seconds at 120 F and dried using air blow off for 30 seconds at 68 F. Coupons were allowed to dry for a half an hour and then reweighed a final time. Efficiencies were calculated.

## Results:

### Summary:

<b>Substrates:</b>	Stainless Steel				
<b>Contaminants:</b>	Oil				
<b>Company Name:</b>	<b>Product Name:</b>	<b>Conc.:</b>	<b>Efficiency:</b>	<b>Effective:</b>	<b>Observations:</b>
BetzDearborne Laboratories Inc	Custom Clean N CC 2278	100	97.09	<input checked="" type="checkbox"/>	
Chemtronics Inc	Super Bio Wash	100	7.75	<input type="checkbox"/>	
Buckeye International	Work Out	5	96.74	<input checked="" type="checkbox"/>	
Delta Omega Technologies Ltd	Attar D(R3)	5	96.07	<input checked="" type="checkbox"/>	
Chemkleen International Inc.	CT 1 Multipurpose Cleaner	5	96.61	<input checked="" type="checkbox"/>	
Equinox Products	Natural Solutions	5	36.08	<input type="checkbox"/>	
Hurri Kleen Corportion	HurriSafe - Hot Immersion Degreaser	5	99.02	<input checked="" type="checkbox"/>	
Heatbath Corporation	MultiKleen LX 1573	5	93.70	<input checked="" type="checkbox"/>	

Conclusion: Six out of the eight products were effective at removing the products at an efficiency rate of over 93%