

CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 2004
 DateRun: 01/27/2004
 Experimenters: Dave Hout
 ClientType: Lab
 ProjectNumber: Project #1
 Substrates: Stainless Steel
 PartType: Coupon
 Contaminants: Oil
 Cleaning Methods: Immersion/Soak
 Analytical Methods: Gravimetric

Purpose: Laboratory evaluations of alternative cleaning products

Experimental Procedure: Basic cleaning performance testing was conducted using ASTM G122 as the bases for cleaning. Six products were heated to 130 F on a hot plate and two products were used at full strength. Twenty-four preweighed coupons were coated with Oil - Benecyn B - 5186 and allowed to dry for a half an hour and reweighed. Three coupons were cleaned in each solution for 5 minutes using stir-bar-agitation, rinsed in a tap water bath for 15 seconds at 120 F and dried using air blow off for 30 seconds at 68 F. Coupons were allowed to dry for a half an hour and then reweighed a final time. Efficiencies were calculated.

Results:

Summary:

Substrates:	Stainless Steel				
Contaminants:	Oil				
Company Name:	Product Name:	Conc.:	Efficiency:	Effective:	Observations:
BetzDearborne Laboratories Inc	Custom Clean N CC 2278	100	97.68	<input checked="" type="checkbox"/>	
Chemtronics Inc	Super Bio Wash	100	18.11	<input type="checkbox"/>	
Buckeye International	Work Out	5	98.10	<input checked="" type="checkbox"/>	
Delta Omega Technologies Ltd	Attar D(R3)	5	99.17	<input checked="" type="checkbox"/>	
Equinox Products	Natural Solutions	5	52.92	<input type="checkbox"/>	
Hurri Kleen Corpotion	HurriSafe - Hot Immersion Degreaser	5	99.35	<input checked="" type="checkbox"/>	
Heatbath Corporation	MultiKleen LX 1573	5	99.54	<input checked="" type="checkbox"/>	

Conclusion: Six out of the eight products were effective at removing the contaminant at an efficiency rate of over 94%.