

# CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 2004  
DateRun: 03/01/2004  
Experimenters: Dave Hout  
ClientType: Lab  
ProjectNumber: Project #1  
Substrates: Aluminum  
PartType: Coupon  
Contaminants: Coatings  
Cleaning Methods: Immersion/Soak  
Analytical Methods: Gravimetric

Purpose: Laboratory evaluations of alternative cleaning products

Experimental Procedure: Basic cleaning performance testing was conducted using ASTM G122 as the bases for cleaning. Two products were used at full strength and two others were heated to 130 F on a hot plate. Twelve preweighed coupons were coated with PPG Industries Hi Gord 1035 and allowed to dry for a half an hour and reweighed. Three coupons were cleaned in each solution for 5 minutes using stir-bar-agitation, rinsed in a tap water bath for 15 seconds at 120 F and dried using air blow off for 30 seconds at 68 F. Coupons were allowed to dry for a half an hour and then reweighed a final time. Efficiencies were calculated.

Results:

Summary:

<b>Substrates:</b>	Aluminum				
<b>Contaminants:</b>	Coatings				
<b>Company Name:</b>	<b>Product Name:</b>	<b>Conc.:</b>	<b>Efficiency:</b>	<b>Effective:</b>	<b>Observations:</b>
Chemtronics Inc	Super Bio Wash	100	99.57	<input checked="" type="checkbox"/>	
Man Gill Chemical Company	Gillite 1156	100	104.02	<input type="checkbox"/>	
Hubbard Hall Inc	Ram Charger	5	103.75	<input type="checkbox"/>	
Chemkleen International Inc.	CT 1 Multipurpose Cleaner	5	98.18	<input checked="" type="checkbox"/>	

Conclusion: Two products were effective at removing the contaminants at an efficient rate of over 98%. The other two may have started to attack the aluminum coupons as the overall efficiency was in excess of 103%.