

# CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 2004  
 DateRun: 05/04/2004  
 Experimenters: Dave Hout  
 ClientType: Lab  
 ProjectNumber: Project #1  
 Substrates: Aluminum  
 PartType: Coupon  
 Contaminants: Resins/Rosins  
 Cleaning Methods: Immersion/Soak  
 Analytical Methods: Gravimetric

Purpose: Laboratory evaluations of alternative cleaning products

Experimental Procedure: Basic cleaning performance testing was conducted using ASTM G122 as the bases for cleaning. Three products were used at full strength and four products were heated to 130 F on a hot plate. Twenty-one preweighed coupons were coated with Ashland Acrylic Resin Aroset 1872 Z40 (108-88-33, 141-78-6, 142-82-5, 67-63-2) and allowed to dry for a half an hour and reweighed. Three coupons were cleaned in each solution for 5 minutes using stir-bar-agitation, rinsed in a tap water bath for 15 seconds at 120 F and dried using air blow off for 30 seconds at 68 F. Coupons were allowed to dry for a half an hour and then reweighed a final time. Efficiencies were calculated.

Results:

Summary:

<b>Substrates:</b>	Aluminum				
<b>Contaminants:</b>	Resins/Rosins				
<b>Company Name:</b>	<b>Product Name:</b>	<b>Conc.:</b>	<b>Efficiency:</b>	<b>Effective:</b>	<b>Observations:</b>
US Polychem Corporation	Polychem A 2000 P	5	19.54	<input type="checkbox"/>	
ISP Technologies	Ship Shape Resin Cleaner	100	-40.96	<input type="checkbox"/>	
Invista S.a.r.l	Flexisolv DBE 3 ester	100	49.25	<input type="checkbox"/>	
EcoLink	VG 151	100	-60.87	<input type="checkbox"/>	
Church & Dwight Co Inc.	Armakleen E 2001	5	-21.43	<input type="checkbox"/>	
US Polychem Corporation	Polychem Ultra CR	5	-17.55	<input type="checkbox"/>	
Brulin Corporation	Formula 815 MX	5	-29.55	<input type="checkbox"/>	

Conclusion: All products were ineffective at removing the contaminants.