

CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 2007
 DateRun: 03/08/2007
 Experimenters: Jason Marshall, Shweta Bansal
 ClientType: Jewelry Mfr
 ProjectNumber: Project #1
 Substrates: Stainless Steel
 PartType: Coupon
 Contaminants: Buffing/Polishing Compounds
 Cleaning Methods: Immersion/Soak
 Analytical Methods: Gravimetric
 Purpose: To evaluate semi-aqueous products in an attempt to increase cleaning times.

Experimental Procedure: Eight products were selected from the lab's database, www.cleansolutions.org, based on past testing effectiveness and compatibility with substrates and equipment. Four products were diluted to 10% using DI water in 600 ml beakers and the other four were used at full strength. Each solution was heated to 130 F on a hot plate.

Twenty-four preweighed coupons were coated with Jackonslea Grey Color 305 A (1344-28-1) by heating the buffing compound to facilitate transfer to the stainless-steel coupons. Once cooled, coupons were weighed again to determine the amount of buffing compound applied. Three coupons were cleaned in each solution for 5 minutes using stir-bar agitation. Coupons were rinsed for 15 seconds in 120 F tap water and dried using compressed air at room temperature for 30 seconds. Coupons were weighed a third time to determine the amount of soil remaining and efficiencies were calculated for each coupon cleaned.

Results: Seven of the eight products removed over 85% of the buffing compound within 5 minutes of immersion cleaning. Four of these removed over 94%. The table lists the amount of buffing compound applied, the amount remaining after cleaning and the efficiency for each coupon cleaned.

Cleaner	Initial wt	Final wt	% Removed
SC Supersolv	0.2060	0.0459	77.72
	0.2034	0.0012	99.41
	0.4942	0.1112	77.50
Bio T Max	0.2996	0.0151	94.96
	0.2861	0.0105	96.33
	0.1876	0.0165	91.20
Solsafe 245	0.1825	0.0084	95.40
	0.2511	0.0046	98.17
	0.3870	0.0048	98.76
DS 104	0.3846	0.0401	89.57
	0.2890	0.0265	90.83
	0.2447	0.0393	83.94
Optisolv OP7171	0.3434	0.1085	68.40
	0.4844	0.1820	62.43
	0.3385	0.0627	81.48
Optisolv OP7168	0.4535	0.0125	97.24
	0.5022	0.0392	92.19
	0.4792	0.0092	98.08
Soy Gold 2000	0.2434	0.0290	88.09
	0.5075	0.0593	88.32
	0.5400	0.0373	93.09
D Greeze 500 Lo	0.4888	0.0161	96.71
	0.5350	0.0185	96.54
	0.6353	0.0103	98.38

Summary:

Substrates:	Stainless Steel					
Contaminants:	Buffing/Polishing Compounds					
Company Name:	Product Name:	Conc.:	Efficiency:	Effective:	Observations:	

CLEANING LABORATORY EVALUATION SUMMARY

Gemtek Products	SC Supersolve Safety Solvent	10	84.88	<input checked="" type="checkbox"/>	
Bio Chem Systems	Bio T Max	100	94.16	<input checked="" type="checkbox"/>	
Bio Chem Systems	Solsafe 245	100	97.44	<input checked="" type="checkbox"/>	
Dysol	DS 104 Wipe Solvent	100	88.11	<input checked="" type="checkbox"/>	
Kyzen Corporation	Optisolv OP7171	10	70.11	<input type="checkbox"/>	
Kyzen Corporation	Optisolv OP7168	10	95.84	<input checked="" type="checkbox"/>	
AG Environmental Products	Soy Gold 2000	10	89.83	<input checked="" type="checkbox"/>	
Transene Company, Inc.	D Greeze 500 LO	100	97.21	<input checked="" type="checkbox"/>	

Conclusion: The seven effective products will be tested at shorter times using ultrasonic energy.