

# CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 2007  
 DateRun: 08/20/2007  
 Experimenters: Jason Marshall, Shweta Bansal, Andrea Cheeseman  
 ClientType: General  
 ProjectNumber: Project #2  
 Substrates: Plastic  
 PartType: Coupon  
 Contaminants: Waxes  
 Cleaning Methods: Mechanical Agitation  
 Analytical Methods: Visual  
 Purpose: To evaluate full strength products at 10 minutes.

Experimental Procedure: The products from the previous trials were retested at 100% dilution and 10 minutes of stripping. Full vinyl tile coupons (12"x12") were coated with the Johnson Wax Show Place floor coating using a paint brush. The coating was allowed to dry for an hour. After completely dry, additional coats were applied. A total of four coats were used.

Initially, each solution was applied to one tile and allowed to soak for 10 minutes. At the end of the soaking, the tile was stripped manually using sections of the scrubbing pad. During scrubbing, hot water was added to the tile and stripping solvent, simulating the procedure witnessed during an on-site visit to the client's facility. Observations were recorded on the effectiveness of the strippers. In addition, three lab personnel independently ranked the strippers for performance. An average of the three assessments were made.

Results: 100% Solvent and 10 minutes

Manufacturer	Product	Ranking			
		1= Most Efficient; 19= Least Efficient			
	Employee	1	2	3	Overall Ave
Abatement Technologies	Citrus Pure Remover	16	9	14	13
Bio-Kleen	Super Stripper D1:3	7	5	7	6.3
Bio-Kleen	Super Stripper D1:5	7	5	7	6.3
Bi-O-Kleen	SL-100	14	17	13	14.7
The Clean Environment Co	Cycle-Strip	13	12	15	13.3
Ecolink	Safe-Strip	2	6	5	4.3
EnvirOx, LLC	Grout-Safe	18	15	18	17
Finger Lakes Chemicals	Graffiti Remover	3	7	3	4.3
Finger Lakes Chemicals	Resineater	8	8	8	8
Franmar	Soy-Gel	1	1	1	1
Franmar	Soy-Strip	9	18	9	12
Gemtek	SC Maxi Solve	4	3	4	3.7
Green Products, LLC	Amaizeing	5	11	6	7.3
Inland Technologies	Citra-Safe	17	13	12	14
Inland Technologies	EP 921	10	14	17	13.7

# CLEANING LABORATORY EVALUATION SUMMARY

SoySolv Ind. Products	SoySolv	15	4	16	11.7
Spartan	Graffiti Remover SAC RTU	12	16	11	13
Spartan	Green Solutions	6	2	2	3.3
Vertec	Ink Zapper	11	10	10	10.3

Summary:

<b>Substrates:</b>	Plastic				
<b>Contaminants:</b>	Waxes				
<b>Company Name:</b>	<b>Product Name:</b>	<b>Conc.:</b>	<b>Efficiency:</b>	<b>Effective:</b>	<b>Observations:</b>
Abatement Technologies	Citrus Pure AS850	100		<input type="checkbox"/>	Rank = 13
Bi-O-Kleen Industries	Super Stripper - Floor Wax Remover	33		<input checked="" type="checkbox"/>	Rank = 6.3
Bi-O-Kleen Industries	Super Stripper - Floor Wax Remover	20		<input checked="" type="checkbox"/>	Rank = 6.3
Bi-O-Kleen Industries	Soy Lube- SL 100	100		<input checked="" type="checkbox"/>	Rank = 14.7
The Clean Environment Co	C-8 Cycle Strip	100		<input type="checkbox"/>	Rank = 13.3
EcoLink	Safe Strip	100		<input checked="" type="checkbox"/>	Rank = 4.3
EnviroX LLC	Grout Safe	100		<input type="checkbox"/>	Rank = 17
Twin Rivers Technologies	Graffiti Remover	100		<input checked="" type="checkbox"/>	Rank = 4.3
Finger Lakes Chemical	FLSC-12 Resineater Sample	100		<input checked="" type="checkbox"/>	Rank = 8
Franmar Chemical	Soy Gel Paint Stripper	100		<input checked="" type="checkbox"/>	Rank = 1
Franmar Chemical	Soy Strip Paint Stripper	100		<input type="checkbox"/>	Rank = 12
Gemtek Products	Safe Care (SC) Maxi Solv	100		<input checked="" type="checkbox"/>	Rank = 3.7
Green Products	aMAIZEing biobased solvent and stripper	100		<input checked="" type="checkbox"/>	Rank = 7.3
Inland Technologies Inc	Citrasafe	100		<input type="checkbox"/>	Rank = 14
Inland Technologies Inc	EP 921	100		<input type="checkbox"/>	Rank = 13.7
SoySolv Industrial Products	SoySolv industrial solvent	100		<input type="checkbox"/>	Rank = 11.7
Spartan Chemical Company	Graffiti Remover SAC	100		<input type="checkbox"/>	Rank = 13
Spartan Chemical Company	Green Solutions Floor Stripper	100		<input checked="" type="checkbox"/>	Rank = 3.3
Vertec BioSolvents	Ink Zapper	100		<input checked="" type="checkbox"/>	Rank = 10.3

Conclusion:

The products will next be assessed for odor levels.