

CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 2004
 DateRun: 07/05/2004
 Experimenters: Heidi Wilcox
 ClientType: Lab
 ProjectNumber: Project #1
 Substrates: Aluminum
 PartType: Coupon
 Contaminants: Oil
 Cleaning Methods: Immersion/Soak
 Analytical Methods: Gravimetric
 Purpose: Laboratory evaluations of alternative cleaning products
 Experimental Procedure: Basic cleaning performance testing was conducted using ASTM G122 as the bases for cleaning.
 Cleaning: 5 min. immersion cleaning at 96 F with stir-bar agitation
 NO Rinsing
 Drying: 30 sec. Air blow off using hose
 Contaminant:
 Oil Hall Company Plashall ESO Cas# 8013-07-8
 Substrate 2 " x 2" aluminum coupons

Results:

Summary:

Substrates:	Aluminum				
Contaminants:	Oil				
Company Name:	Product Name:	Conc.:	Efficiency:	Effective:	Observations:
Petroferm Inc	Lenium ES	100	99.72	<input checked="" type="checkbox"/>	
Invista S.a.r.l	Flexisolv DBE 6 ester	100	99.71	<input checked="" type="checkbox"/>	

Conclusion: All were effective.