

# CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 2004  
 DateRun: 07/06/2004  
 Experimenters: Heidi Wilcox  
 ClientType: Lab  
 ProjectNumber: Project #1  
 Substrates: Steel  
 PartType: Coupon  
 Contaminants: Coatings  
 Cleaning Methods: Immersion/Soak  
 Analytical Methods: Gravimetric  
 Purpose: Laboratory evaluations of alternative cleaning products  
 Experimental Procedure: Basic cleaning performance testing was conducted using ASTM G122 as the bases for cleaning.  
 Cleaning: 5 min. immersion cleaning at 96 F with stir-bar agitation.  
 NO Rinsing  
 Drying: 30 sec. Air blow off using hose  
 Contaminant:  
 Coating - Rochester Midland Corp - RI 780 Rust Prev Coating  
 Cas# 8052-41-2, 95-63-6

**Results:**

**Summary:**

<b>Substrates:</b>	Steel				
<b>Contaminants:</b>	Coatings				
<b>Company Name:</b>	<b>Product Name:</b>	<b>Conc.:</b>	<b>Efficiency:</b>	<b>Effective:</b>	<b>Observations:</b>
Petroferm Inc	Lenium CP (no longer available)	100	98.95	<input checked="" type="checkbox"/>	
Petroferm Inc	Lenium ES	100	100.63	<input checked="" type="checkbox"/>	
Invista S.a.r.l	Flexisolv DBE 6 ester	100	100.60	<input checked="" type="checkbox"/>	

**Conclusion:** All cleaned effectively.