

# CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 2007

DateRun: 06/28/2007

Experimenters: Shweta Bansal

ClientType: Lab

ProjectNumber: Project #1

Substrates: Aluminum

PartType: Coupon

Contaminants: Adhesive

Cleaning Methods: Ultrasonics

Analytical Methods: Gravimetric

Purpose: Laboratory evaluations of alternative cleaning products

Experimental Procedure: Basic cleaning performance testing was conducted using ASTM G122 as the bases for cleaning.  
Cleaning: 5 min Ultrasonics cleaning at 130 F.  
Rinsing with Tap Water  
Drying: 30 s50 Air blow off using hose and outlet on bench  
Contaminant  
Green Glue  
Substrate 2"x 4"x 0.06" Aluminum Coupons

## Results:

### Summary:

<b>Substrates:</b>	Aluminum				
<b>Contaminants:</b>	Adhesive				
<b>Company Name:</b>	<b>Product Name:</b>	<b>Conc.:</b>	<b>Efficiency:</b>	<b>Effective:</b>	<b>Observations:</b>
Gemtek Products	SC Supersolve Safety Solvent	5	84.17	<input type="checkbox"/>	
US Polychem Corporation	Polyspray Jet 790 P	5	78.06	<input type="checkbox"/>	
International Products Corporation	Micro 90 Conc.	5	81.87	<input type="checkbox"/>	
Magnaflux	Daraclean 238	5	24.40	<input type="checkbox"/>	
Gemtek Products	SC EZ Solv Safety Solvent	5	2.76	<input type="checkbox"/>	
US Polychem Corporation	Polychem A 2000 P	5	50.35	<input type="checkbox"/>	

### Conclusion: