

# CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 2007  
 DateRun: 07/10/2007  
 Experimenters: Shweta Bansal  
 ClientType: Lab  
 ProjectNumber: Project #1  
 Substrates: Aluminum  
 PartType: Coupon  
 Contaminants: Inks  
 Cleaning Methods: Immersion/Soak  
 Analytical Methods: Gravimetric  
 Purpose: Laboratory evaluations of alternative cleaning products  
 Experimental Procedure: Basic cleaning performance testing was conducted using ASTM G122 as the bases for cleaning.  
 Cleaning: 5 min Immersion Soak cleaning at 130 F with stir-bar agitation.  
 Rinsing with Tap Water  
 Drying: 30 s50 Air blow off using hose and outlet on bench  
 Contaminant Mix-Opake Plastisol Inks  
 Substrate 2"x 4"x 0.06" Aluminum Coupons

Results:

Summary:

<b>Substrates:</b>	Aluminum				
<b>Contaminants:</b>	Inks				
<b>Company Name:</b>	<b>Product Name:</b>	<b>Conc.:</b>	<b>Efficiency:</b>	<b>Effective:</b>	<b>Observations:</b>
Chemtronics Inc	Super Bio Wash	5	7.50	<input type="checkbox"/>	
Church & Dwight Co Inc.	Armakleen E 2001	5	2.18	<input type="checkbox"/>	
Ausimont USA Inc	Perfluorosolv PFS 1	5	3.31	<input type="checkbox"/>	
Warren Chemical Company	Sea Wash Blue	5	2.93	<input type="checkbox"/>	

Conclusion: