



CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 2007
 DateRun: 07/23/2007
 Experimenters: Shweta Bansal
 ClientType: Lab
 ProjectNumber: Project #1
 Substrates: Aluminum
 PartType: Coupon
 Contaminants: Oil
 Cleaning Methods: Immersion/Soak
 Analytical Methods: Gravimetric
 Purpose: Laboratory evaluations of alternative cleaning products
 Experimental Procedure: Basic cleaning performance testing was conducted using ASTM G122 as the bases for cleaning.
 Cleaning: 5 min Immersion Soak cleaning at 130 F with stir-bar agitation.
 Rinsing with Tap Water
 Drying: 30 s50 Air blow off using hose and outlet on bench
 Contaminant Soybean
 Substrate 2"x 4"x 0.06" Aluminum Coupons

Results:

Summary:

Substrates:	Aluminum				
Contaminants:	Oil				
Company Name:	Product Name:	Conc.:	Efficiency:	Effective:	Observations:
Valtech Corporation	Valtron SP 2275	5	85.94	<input checked="" type="checkbox"/>	
Magnaflux	Daraclean 235	5	87.28	<input checked="" type="checkbox"/>	
Oakite Products	Inproclean 2500	5	87.32	<input checked="" type="checkbox"/>	
Gemtek Products	SC Supersolve Safety Solvent	5	85.41	<input checked="" type="checkbox"/>	

Conclusion: