

# CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 2009  
DateRun: 03/23/2009  
Experimenters: Jason Marshall, Junhee Cho  
ClientType: Chemical Company  
ProjectNumber: Project #1  
Substrates: Aluminum  
PartType: Coupon  
Contaminants: Cutting/Tapping Fluids  
Cleaning Methods: Manual Wipe  
Analytical Methods: Gravimetric

Purpose: To evaluate supplied product for light oil removal as compared to acetone.

Experimental Procedure: One supplied product and acetone were used at full strength and room temperature. Six preweighed 6061 H6 aluminum coupons were coated with the Steco Corporation Tap Magic cutting fluid using a handheld swab. Coupons were weighed a second time to determine the amount of fluid added to the surface.

Three coupons were placed in the Gardner Straight Line Washability unit. Cleaning solution was applied to the surface using a plastic squeeze bulb. A reinforced Kimberly Clark Wypall X60 paper towel was attached to the cleaning sled and soaked with the same cleaning product. Cleaning was conducted for 20 cycles. Final weights were recorded, and efficiencies calculated for each coupon cleaned.

Results:

Cleaner	Initial wt	Final wt	% Removed
SWC 100			
	0.4207	0.0195	95.36
	0.3519	0.0289	91.79
	0.3202	0.0183	94.28
Acetone			
	0.3033	0.0175	94.23
	0.2289	0.0124	94.58
	0.2245	0.0156	93.05

Summary:

<b>Substrates:</b>		Aluminum				
<b>Contaminants:</b>		Cutting/Tapping Fluids				
Company Name:		Product Name:	Conc.:	Efficiency:	Effective:	Observations:
Environmental Solution Products Inc		SWC 100	100	93.81	<input checked="" type="checkbox"/>	
Fisher Scientific		Acetone (CAS: 67-64-1)	100	93.95	<input checked="" type="checkbox"/>	

Conclusion:

The next step will be to record the time required to remove all of the cutting fluid from the aluminum surface.