

CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 2009
 DateRun: 03/03/2009
 Experimenters: Daniel Pina
 ClientType: Lab
 ProjectNumber: Project #1
 Substrates: Steel
 PartType: Coupon
 Contaminants: None
 Cleaning Methods: Immersion/Soak
 Analytical Methods: Compatibility, Gravimetric

Purpose: To see if these 2 specific cleaning products at a desired concentration would erode the surface that the product is trying to treat.

Experimental Procedure: Basic cleaning performance testing was conducted using ASTM G122 as the bases for cleaning. Clean off steel coupons until you can get as close to the original weight. Then you will go and place the coupons in the beaker where the solution was created and leave it soaked with the solution for 24hrs. Remeasure the coupons and see if the weight has changed or not to determine if the sample has been eroded or `not.

Cleaner	Initial wt	Final wt	Difference
Brulin Corporation aqu avantage	32.0350	32.0370	0.00
	32.1865	32.1895	0.00
	31.8947	31.8977	0.00
magnaflux daraclean 238	31.6405	31.5865	-0.05
	32.1498	32.1550	0.01
	31.8738	31.8314	-0.04

Summary:	Substrates:	Steel				
	Contaminants:	None				
	Company Name:	Product Name:	Conc.:	Efficiency:	Effective:	Observations:
	Brulin Corporation	Aquavantage 1400	10	0.00	<input checked="" type="checkbox"/>	
	Magnaflux	Daraclean 238	10	0.00	<input checked="" type="checkbox"/>	

Conclusion: The solution did not erode the surfaces of the coupon it must off been from the last test that the solution removed some of the soil that the coupon must of have before doing the test that was reported on trial number 277.