

CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 2003
DateRun: 01/29/2003
Experimenters: Jason Marshall
ClientType: Manufactures parts for Semi-Conductor Industry
ProjectNumber: Project #1
Substrates: Ceramics
PartType: Coupon
Contaminants: Waxes
Cleaning Methods: Immersion/Soak
Analytical Methods: Gravimetric
Purpose: To evaluate products on the sixth supplied wax

Experimental Procedure: Two products were selected from the laboratories database of testing results based on client supplied data. Three other products were also selected based on success in previous trial. All six products were used at full strength in 600 ml beakers. The products were heated to 130 F on a hot plate. Fifteen preweighed ceramic coupons were coated with client supplied Areenco Crystalbond 509 wax. The wax was melted using a Master Appliance heat gun in a beaker and applied directly to the coupons. The coupons were allowed to cool to room temperature before weighing a second time. Three coupons were cleaned in each solution for 10 minutes using stir-bar agitation. Coupons were rinsed in tap water for 15 seconds at 120 F, followed by air blow off at room temperature. Once dry, coupons were weighed a final time and efficiencies for each cleaner were calculated. The most successful cleaner was then used for 30 minutes.

Results: None of the cleaners were able to remove over 15% of the Crystalbond during the 10 minute cleaning. One product, DS-108 was tested at an extended time. This resulted in about 60% of the Crystalbond 509 being removed. An increase in temperature, time or agitation would help to increase the cleaning efficiency. The table below lists the amount of Crystalbond applied and removed.

Table 1. Crystalbond Removal

Cleaner	Initial wt	Final wt	% Removed
Opti Clear	2.6864	2.6873	-0.03
	1.0942	1.0918	0.22
	0.9742	0.9749	-0.07
Citrikleen XPC	0.9675	0.9652	0.24
	1.1464	1.1428	0.31
	1.0141	1.0126	0.15
Bio T 200 A	1.2436	1.2471	-0.28
	1.3766	1.3471	2.14
	1.2756	1.2781	-0.20
Crystal Bond 590 S	0.7117	0.7130	-0.18
	1.5351	1.5164	1.22
	1.7944	1.7952	-0.04
Dynamold DS 108	2.6873	2.4000	10.69
10 Min	1.0918	0.9746	10.73
	0.9749	0.8468	13.14
Dynamold DS 108	0.9746	0.5016	48.53
30 Min	0.8468	0.3335	60.62
	0.9652	0.2848	70.49

Summary:

Substrates:	Ceramics				
Contaminants:	Waxes				
Company Name:	Product Name:	Conc.:	Efficiency:	Effective:	Observations:
National Diagnostic	Opti Clear	100	0.04	<input type="checkbox"/>	
Pentone Corporation	Citrikleen XPC	100	0.23	<input type="checkbox"/>	

CLEANING LABORATORY EVALUATION SUMMARY

Bio Chem Systems	Bio T 200 A	100	0.56	<input type="checkbox"/>	
Aremco Products Inc	Crystalbond 590 S	100	0.33	<input type="checkbox"/>	
Dysol	DS 108 Wipe Solvent	100	11.52	<input type="checkbox"/>	10 minute cleaning
Dysol	DS 108 Wipe Solvent	100	59.88	<input checked="" type="checkbox"/>	30 minute cleaning

Conclusion:

The next phase of testing will begin by cleaning supplied parts.