

# CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 2003  
 DateRun: 02/27/2003  
 Experimenters: Jason Marshall  
 ClientType: Medical Instrument Mfr  
 ProjectNumber: Project #1  
 Substrates: Plastic  
 PartType: Coupon  
 Contaminants: Hucker's Soil  
 Cleaning Methods: Immersion/Soak  
 Analytical Methods: Gravimetric  
 Purpose: To evaluate alternative cleaners to supplied current cleaners for Hucker's Soil removal from plastic substrates.

Experimental Procedure: Six cleaners were selected from the laboratory's database of testing based on supplied client information. All six were diluted to 5% using DI water in 600 ml beakers. The two supplied cleaners were diluted to concentrations used by client in 600 ml beakers. All eight cleaners were heated to 130 F on a hot plate. Twenty-four preweighed plastic coupons were coated with the supplied Hucker' Soil (Creamy Peanut Butter, Salted Butter, Wheat gluten, Egg Yolk, Evaporated milk, DI water, Printer's ink with boiled linseed oil, India Ink, Saline Solution) using a hand held swab and allowed to dry. Coupons were weighed again to determine the amount of soil added. Three coupons were cleaned in each solution for 5 minutes using stir-bar agitation at 130 F. Rinsing was performed for 15 seconds in tap water at 120 F and followed by drying with a Master Appliance heat gun for 30 seconds at 500 F. Once coupons cooled to room temperature, final weights were recorded and efficiencies were calculated.

Results: Five of the six selected products performed better than the two supplied products. Four of these products removed over 90% of the Hucker's soil from the plastic coupons. The table below lists the amount of soil applied and removed for each coupon.

Cleaner	Initial wt	Final wt	% Removed
Sea Wash 8	0.5427	0.0675	87.56
	0.2955	0.0288	90.25
	0.4932	0.0362	92.66
Ozzy Juice SW3	0.3075	0.0534	82.63
	0.2673	0.0313	88.29
	0.1937	0.0425	78.06
SC Aircraft & Metal	0.4544	0.0554	87.81
	0.1820	0.0326	82.09
	0.2821	0.0147	94.79
United 450 All Clear	0.2877	0.0063	97.81
	0.5779	0.0185	96.80
	0.4547	0.0293	93.56
Micro 90	0.2512	0.0008	99.68
	0.3372	0.0194	94.25
	0.1741	0.0183	89.49
Aluminum Aerowash	0.3133	0.0170	94.57
	0.3219	0.0259	91.95
	1.0261	0.0140	98.64
Simple Green D	0.1571	0.0269	82.88
	0.2494	0.0396	84.12
	0.3770	0.0551	85.38
Lestoil	0.3413	0.0444	86.99
	0.2609	0.0385	85.24
	0.3718	0.0617	83.41

Summary:

<b>Substrates:</b>	Plastic
--------------------	---------

## CLEANING LABORATORY EVALUATION SUMMARY

<b>Contaminants:</b>		Hucker's Soil			
<b>Company Name:</b>	<b>Product Name:</b>	<b>Conc.:</b>	<b>Efficiency:</b>	<b>Effective:</b>	<b>Observations:</b>
Warren Chemical Company	Sea Wash 8 No Force	5	90.16	<input checked="" type="checkbox"/>	
Chem Free Corporation	SW-3 Ozzy Juice (Improved Low Odor)	5	82.99	<input type="checkbox"/>	
Gemtek Products	SC Aircraft & Metal Cleaner Super Concentrate	5	88.23	<input checked="" type="checkbox"/>	
United Laboratories International	United 450 All Clear	5	96.06	<input checked="" type="checkbox"/>	
International Products Corporation	Micro 90 Conc.	5	94.47	<input checked="" type="checkbox"/>	
Magnum Research Corporation	Aluminum Aerowash	5	95.05	<input checked="" type="checkbox"/>	
Simple Green	Simple Green D	10	84.13	<input type="checkbox"/>	
Clorox Company	Lestoil	2	85.21	<input checked="" type="checkbox"/>	

**Conclusion:**

The five successful products (United 450 All Clear, Aluminum Aerowash, Micro 90, Sea Wash 8, SC Aircraft & Metal) will be used in the next trial on supplied tubing. The two client supplied products will also be tested.