

# CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 2004  
 DateRun: 08/29/2004  
 Experimenters: Jason Marshall  
 ClientType: Jewelry Mfr  
 ProjectNumber: Project #1  
 Substrates: Brass  
 PartType: Part  
 Contaminants: Buffing/Polishing Compounds  
 Cleaning Methods: Vapor Degreasing  
 Analytical Methods: Photography, Visual

Purpose: To evaluate top two drop-in solvent cleaners on supplied parts.

Experimental Procedure: Two products from the previous trials were heated to boiling in a beaker vapor degreaser. One part was immersed into the solvent and cleaned for five minutes. At the end of the cleaning the part was removed from the vapors and observed visually for cleaning results.  
 Parts were photographed before and after cleaning.

Results: Both solvents removed a majority of the contaminant from the supplied parts within the five minutes. However, neither product removed all of the buffing/milling contaminants. Lenium ES was more effective than the Kyzen Metalnox M6960. The dirty and clean parts are shown in the photographs.

Summary:

<b>Substrates:</b>	Brass				
<b>Contaminants:</b>	Buffing/Polishing Compounds				
<b>Company Name:</b>	<b>Product Name:</b>	<b>Conc.:</b>	<b>Efficiency:</b>	<b>Effective:</b>	<b>Observations:</b>
Petroferm Inc	Lenium ES	100	0.00	<input checked="" type="checkbox"/>	
Kyzen Corporation	Metalnox M6960	100	0.00	<input type="checkbox"/>	

Conclusion: Soaking the parts in the hot solvent with ultrasonics followed by a vapor rinse may result in an improvement in cleaning efficiency. Additional parts would be needed to perform more testing on these solvents as well as the other products.