

# CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 2005

DateRun: 05/05/2005

Experimenters: Chang Won

ClientType: Lab

ProjectNumber: Project #1

Substrates: Wood

PartType: Coupon

Contaminants: Paints

Cleaning Methods: Manual Wipe

Analytical Methods: Gravimetric, Visual

Purpose: Laboratory evaluations of alternative cleaning products

Experimental Procedure: Basic cleaning performance testing was conducted using ASTM G122 as the bases for cleaning.  
Basic cleaning performance testing was conducted using ASTM G122 as the bases for cleaning.  
Cleaning: Brush on gel/paste strippers in one thick coat.  
Run Time: Let sit 3 hours (180min)  
Removal: manual scrape with plastic spatula/scrapper (Home Depot general paint scraper)  
Drying: 72-hour dry time to allow for evaporation of strippers from wood.

## Results:

### Summary:

<b>Substrates:</b>	Wood				
<b>Contaminants:</b>	Paints				
<b>Company Name:</b>	<b>Product Name:</b>	<b>Conc.:</b>	<b>Efficiency:</b>	<b>Effective:</b>	<b>Observations:</b>
Vertec BioSolvents	Take Off Green	100	9.82	<input type="checkbox"/>	
Savogran Company	SI #4 Coating Remover	100	7.60	<input type="checkbox"/>	
Sterling Clark Lurton Corp	Thin X - Clean Air Paint Thinner	100	26.26	<input type="checkbox"/>	
Pentone Corporation	Citrikleen XPC	100	6.79	<input type="checkbox"/>	

### Conclusion: