

# CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 2005  
 DateRun: 05/05/2005  
 Experimenters: Chang Won  
 ClientType: Lab  
 ProjectNumber: Project #1  
 Substrates: Wood  
 PartType: Coupon  
 Contaminants: Paints  
 Cleaning Methods: Manual Wipe  
 Analytical Methods: Gravimetric, Visual  
 Purpose: Laboratory evaluations of alternative cleaning products  
 Experimental Procedure: Basic cleaning performance testing was conducted using ASTM G122 as the bases for cleaning.  
 Basic cleaning performance testing was conducted using ASTM G122 as the bases for cleaning.  
 Cleaning: Brush on gel/paste strippers in one thick coat.  
 Run Time: Let sit 3 hours (180min)  
 Removal: manual scrape with plastic spatula/scrapper (Home Depot general paint scraper)  
 Drying: 72-hour dry time to allow for evaporation of strippers from wood.

## Results:

### Summary:

<b>Substrates:</b>	Wood				
<b>Contaminants:</b>	Paints				
<b>Company Name:</b>	<b>Product Name:</b>	<b>Conc.:</b>	<b>Efficiency:</b>	<b>Effective:</b>	<b>Observations:</b>
Vertec BioSolvents	Take Off Green	100	9.82	<input type="checkbox"/>	
Savogran Company	SI #4 Coating Remover	100	7.60	<input type="checkbox"/>	
Sterling Clark Lurton Corp	Thin X - Clean Air Paint Thinner	100	26.26	<input type="checkbox"/>	
Pentone Corporation	Citrikleen XPC	100	6.79	<input type="checkbox"/>	

### Conclusion: