CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 2003

DateRun: 03/03/2003

Experimenters: Chang Won

ClientType: Lab

ProjectNumber: Project #1

Substrates: Wood

PartType: Coupon

Contaminants: Paints

Cleaning Methods: Manual Wipe

Analytical Methods: Gravimetric

Purpose: Laboratory evaluations of alternative cleaning products

Experimental Procedure: Basic cleaning performance testing was conducted using ASTM G122 as the bases for cleaning.

Cleaning: Brush on gel/paste strippers in one thick coat.
Run Time: Let sit 3 hours (180min)
Removal: manual scrape with plastic spatula/scraper (Home Depot general paint scraper)
Drying: 72-hour dry time to allow for evaporation of strippers from wood.

Results: 03-WD-PA-5-301
Wood: Poplar 2" x 4" x 1/4"

Summary:

Substrates:	Wood				
Contaminants:	Paints				
Company Name:	**Product Name:**	**Conc.:**	**Efficiency:**	**Effective:**	**Observations:**
Phase III Inc	Biodegradable Paint & Adhesive Remover	100	48.66	☐	
Vertec BioSolvents	Take Off Green	100	152.97	☐	
Savogran Company	SI #4 Coating Remover	100	157.19	☐	
Vertec BioSolvents	VertecBio Gold Unscented Part Cleaner	100	75.19	☑	
EcoLink	Safe Strip	100	76.00	☑	

Conclusion: