

CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 2003
 DateRun: 05/31/2003
 Experimenters: Chang Won
 ClientType: Lab
 ProjectNumber: Project #1
 Substrates: Wood
 PartType: Coupon
 Contaminants: Coatings
 Cleaning Methods: Manual Wipe
 Analytical Methods: Gravimetric
 Purpose: Laboratory evaluations of alternative cleaning products
 Experimental Procedure: Basic cleaning performance testing was conducted using ASTM G122 as the bases for cleaning.
 Cleaning: Brush on gel/paste strippers in one thick coat.
 Run Time: Let sit 1 hour (60min)
 Removal: manual scrape with plastic spatula/scrapper (Home Depot general paint scraper)
 Drying: 72-hour dry time to allow for evaporation of strippers from wood.

Results: 03-WD-PA-6-
Wood-Paint Products

Maple-Poly	SI #4	Peel Away #7	Safety peel	Force 9	Green	Strypeez
Coupon 1	85.10	83.66	83.32	79.64	85.32	82.67
Coupon 2	90.35	82.76	85.34	87.90	78.24	86.28
Coupon 3	84.71	86.84	81.08	85.21	84.56	84.13
Average	86.72	84.42	83.25	84.25	82.71	84.36
Std Dev	3.15	2.14	2.13	4.21	3.89	1.82

Summary:

Substrates:	Wood				
Contaminants:	Coatings				
Company Name:	Product Name:	Conc.:	Efficiency:	Effective:	Observations:
Savogran Company	SI #4 Coating Remover	100	86.72	<input checked="" type="checkbox"/>	
Dumond Chemicals Inc	Peel Away 7	100	84.42	<input checked="" type="checkbox"/>	
Prosoco Inc	Enviro Klean Safety Peel	100	83.25	<input checked="" type="checkbox"/>	
Pollux Company	Force 9	100	84.25	<input checked="" type="checkbox"/>	
Vertec BioSolvents	Take Off Green	100	82.71	<input checked="" type="checkbox"/>	
Savogran Company	Strypeeze	100	84.36	<input checked="" type="checkbox"/>	

Conclusion: