

# CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 2021  
 DateRun: 02/23/2021  
 Experimenters: Edward Judge  
 ClientType: Cleaner Manufacturer  
 ProjectNumber: Project #1  
 Substrates: Glass/Quartz, Chrome  
 PartType: Coupon  
 Contaminants: Glass  
 Cleaning Methods: Manual Wipe  
 Analytical Methods: Gravimetric, Visual

Purpose: To evaluate the efficiency of PathoClean for removing SCL Soil 2 (glass soil) from two substrates.

Experimental Procedure: Six pre-weighed coupons, three of each substrate, for each cleaner were contaminated with one gram of glass soil and air-dried at room temperature for hours. Three coupons of the same substrate were loaded into the Straight-Line Washability (SLW) device, and a KC Wypall reinforced paper towel was attached to the cleaning sled. The Wypall and coupons were each treated with two sprays of the cleaner and run for 20 cycles (equivalent to 30 seconds of cleaning). The pH was logged after testing, and coupons air-dried at room temperature for 24 hours before recording final weights.

Results: PathoClean and Windex both were effective for the removal of glass soil from both glass and chrome substrates. PathoClean averaged 94% for chrome and 84% for glass. Windex averaged 93% for chrome and 99% for glass. Both cleaners are comparable to each other and effectively removed the soil. The pH was 10.

Cleaner	Substrate	Initial wt	Final wt	% Removed	% AVG	% Overall
PathoClean	Chrome	0.9428	0.0820	91.30	93.61	93.70
		1.5877	0.0673	95.76		
		1.1837	0.0739	93.76		
	Glass	0.8972	0.0704	92.15	93.79	
		0.8037	0.0367	95.43		
		0.8757	0.0544	93.79		
Windex	Chrome	1.2414	0.1192	90.40	93.42	96.12
		1.1821	0.0577	95.12		
		1.2239	0.0644	94.74		
	Glass	0.8374	0.0219	97.38	98.81	
		0.9868	0.0024	99.76		
		0.8849	0.0062	99.30		

PathoClean was 5% less effective on glass but was still visually effective and comparable to Windex.

Summary:

<b>Substrates:</b>	Glass/Quartz, Chrome				
<b>Contaminants:</b>	Glass				
<b>Company Name:</b>	<b>Product Name:</b>	<b>Conc.:</b>	<b>Efficiency:</b>	<b>Effective:</b>	<b>Observations:</b>
PathoSans	Pathopure	100	93.70	<input checked="" type="checkbox"/>	
SC Johnson & Son Inc	Windex Glass Original w/ Ammonia-D	100	96.12	<input checked="" type="checkbox"/>	

Conclusion: PathoClean was just as effective, both visually and gravimetrically, as Windex for the removal of glass soil on chrome and glass.