

CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 2021
 DateRun: 09/13/2021
 Experimenters: Edward Judge
 ClientType: Lab
 ProjectNumber: Project #5
 Substrates: Glass/Quartz, Other, Chrome
 PartType: Coupon
 Contaminants: Glass
 Cleaning Methods: Manual Wipe
 Analytical Methods: Gravimetric, Visual
 Purpose: To test the effectiveness of Lysol with Hydrogen Peroxide in the removal of Glass Soil from various substrates.

Experimental Procedure: A Lysol with Hydrogen Peroxide solution was gathered to begin testing. Then, 3 coupons of each substrate (chrome, glass, mirror) were collected and initial weights were taken. Glass Soil was applied to each coupon and allowed to air dry for 24 hours. After the 24 hour dry time, the weights of the newly contaminated coupons were measured. All coupons were placed into a Gardner-scrub Abrasion Tester machine. Wypall cleaning cloths were attached to each of the 3 cleaning blocks used for the test. Each Wypall cloth and all coupons received 2 sprays of the Lysol with Hydrogen Peroxide solution and the Gardner-scrub Abrasion Tester was run for 20 repetitions, simulating 20 manual wipes. Once cleaning concluded, the cleaned coupons were allowed to air dry for 24 hours. After 24 hours, the weights of the cleaned coupons were measured.

Results:

Cleaner	Substrate	Initial wt of cont.	Final wt of cont.	%Cont Removed	% AVG	% Overall
Lysol with Hydrogen Peroxide	Chrome	0.0514	0.0006	98.83	97.44	96.11
		0.0638	0.0023	96.39		
		0.0607	0.0019	96.87		
	Glass	0.0431	0.0010	97.68	95.79	
		0.0452	0.0021	95.35		
		0.0546	0.0031	94.32		
	Mirror	0.0407	0.0014	96.56	95.11	
		0.0403	0.0024	94.04		
		0.0437	0.0023	94.74		

Summary:

Conclusion: Lysol with Hydrogen Peroxide was successful in the removal of Glass Soil from chrome, glass, and mirror substrates.