

# CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 2021  
DateRun: 12/14/2021  
Experimenters: Zoe Lawson  
ClientType: Lab  
ProjectNumber: Project #7  
Substrates: Ceramics, Plastic, Painted metal  
PartType: Coupon  
Contaminants: Hucker's Soil  
Cleaning Methods: Manual Wipe  
Analytical Methods: Gravimetric  
Purpose: Control testing to monitor hucker's soil consistency.

Experimental Procedure: Nine pre-weighed coupons were contaminated with 0.5 grams of Hucker's soil (Evaporated Milk; 26.5%, Creamy Peanut Butter; 17%, Salted Butter; 17%, Stone Ground Wheat Flour; 17%, Linseed Oil; 2.25%, Saline Solution; 5.25%, India Ink; 6.8%, Lemon Juice; 8.2%). Coupons were aged for two hours at room temperature (68°F) before dirty weights were recorded. Coupons of the same substrate were placed into the Straight Line Washability (SLW) unit, three at a time, and treated twice with water. A Wypall was attached to the SLW sled and was also treated twice with water. Each test ran 20 cycles (~30 seconds of cleaning). Coupons were air-dried at room temperature (68°F) overnight before final weights were recorded.

Results:	Cleaner	Substrate	Initial wt of cont.	Final wt of cont.	%Cont Removed	% AVG	% Overall
	Water	Ceramic	0.5015	0.0961	80.84	79.59	79.92
			0.4909	0.1136	76.86		
			0.4557	0.0862	81.08		
		Painted Steel	0.5672	0.1379	75.69	78.87	
			0.4965	0.0902	81.83		
			0.5168	0.1081	79.08		
		Plastic	0.5022	0.1124	77.62	81.3	
			0.4202	0.0679	83.84		
			0.5171	0.0908	82.44		

Summary:

Conclusion: The overall removal percentage for this control test was 79.92%.