

# CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 2023

DateRun: 12/10/2023

Experimenters: Amelia Wagner

ClientType:

ProjectNumber: Project #1

Substrates: Painted metal

PartType: Coupon

Contaminants: DCC-17

Cleaning Methods: Manual Wipe

Analytical Methods: Gravimetric

Purpose: To evaluate the effectiveness of the client's degreasing product compared to other degreasing products on the market.

Experimental Procedure: Two products were tested; Easy Off, and KH-7 (client's product). A total of six coupons were used, three per cleaner, were weighed. The coupons were then soiled with DCC-17 soil. About 0.5 grams of the soil was applied to each coupon by using a swab to apply the soil in a line down the center of the coupon. The weight of the soiled coupons were recorded. Three coupons at a time were then placed in the Gardner Straight Line Washability Unit. Wypall cleaning cloths were attached to the cleaning block used for the test. Each Wypall cloth and all coupons received two sprays of the cleaner (2.5 ml total), and the SLW unit was run for 20 cycles (Equivalent to 30 seconds of cleaning). Final weights were taken after air drying at room temperature.

Cleaner	Initial wt of cont.	Final wt of cont.	%Cont Removed	% AVG
Easy Off	0.0528	0.0054	89.77	87.66
	0.1490	0.0196	86.85	
	0.0828	0.0113	86.35	
KH 7	0.0408	0.0064	84.31	84.76
	0.0861	0.0115	86.64	
	0.0492	0.0082	83.33	

Summary:		<b>Substrates:</b> Painted metal				
		<b>Contaminants:</b> DCC-17				
<b>Company Name:</b>	<b>Product Name:</b>		<b>Conc.:</b>	<b>Efficiency:</b>	<b>Effective:</b>	<b>Observations:</b>
Easy-Off	Easy Off Cleaner Degreaser Heavy Duty		RTU	87.66	<input checked="" type="checkbox"/>	
KH Lloreda SA	KH 7 Super Degreaser		RTU	84.76	<input checked="" type="checkbox"/>	

Conclusion: Both products were effective in removing DCC17 soil from painted metal, and performed comparatively.