

# CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 2023  
 DateRun: 01/08/2024  
 Experimenters: Siddhant Trivedi, Serena Burkinshaw  
 ClientType: Department of Public Works  
 ProjectNumber: Project #2  
 Substrates: Stainless Steel  
 PartType: Coupon  
 Contaminants: Asphalt  
 Cleaning Methods: Immersion/Soak  
 Analytical Methods: Gravimetric  
 Purpose: To find an effective alternative cleaner to remove asphalt, tar, and staining from road maintenance tools and work truck beds.

Experimental Procedure: Three pre-weighed stainless steel coupons were assigned to each cleaner. A tablespoon of EZ Street Premium Cold Asphalt was placed on each coupon before sandwiching the contaminated coupon between two steel plates. A mid-size compact car (curb weight: 3,186lbs-3,559lbs) rolled over the steel plates five times in a forward motion to compress the asphalt to the coupons which released the oil and grease to allow the gravel to adhere to the substrate. Dirty weights of the coupons were recorded before testing the cleaners using unheated immersion for 20 minutes with a stir bar set to 200rpm. Once removed, each coupon was wiped with a paper towel to remove the dissolved soil and assess efficacy visually before taking final weights.

| Cleaner        | Initial wt of cont. | Final wt of cont. | %Cont Removed | % AVG |
|----------------|---------------------|-------------------|---------------|-------|
| Pave Pro Green | 0.8598              | 0.0174            | 97.98         | 94.66 |
|                | 0.1308              | 0.0169            | 87.08         |       |
|                | 1.4297              | 0.0154            | 98.92         |       |
| Pave Pro Gold  | 0.9355              | 0.0139            | 98.51         | 98.83 |
|                | 1.4056              | 0.0161            | 98.85         |       |
|                | 1.5561              | 0.0139            | 99.11         |       |

Summary:

Conclusion: Both PavePro Green and PavePro Gold are highly effective in removing asphalt from stainless steel substrates.