

CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 2024

DateRun: 09/24/2024

Experimenters: Amelia Wagner

ClientType: Metal Finishing

ProjectNumber: Project #1

Substrates: Carbon Steel

PartType: Coupon

Contaminants: Cutting/Tapping Fluids, Greases, Lubricating/Lapping Oils, Oil, Silicones

Cleaning Methods: Immersion/Soak

Analytical Methods: Colorimeter, Visual

Purpose: To test the efficacy of modified alcohols on provided carbon steel parts

Experimental Procedure: Pre soiled carbon steel flags and caps were provided to the TURI lab by the client. The parts were soiled with corrosion preventatives, silicon based lubricants, water based oil, and grease. Three of each part were tested together as a 'coupon' set. The analytic results of each individual part in a set were averaged together to provide the analytical data point for the coupon sets. Before cleaning, each coupon set were visually observed and had their dirty visual rankings recorded. Each coupon set was analyzed using a cleanspector to measure the amount of fluorescence emitted. The dirty fluorescence levels of each coupon set were recorded. The coupon sets were then subjected to 20 mins of heated immersion at 180F in PnB glycol Ether (stir bar set to 300 rpm). Once removed, each coupon set was dried using a heat gun for about 30 seconds to evaporate the remaining cleaning chemistry. After dried, each coupon set had their clean visual rankings and clean fluorescence levels recorded.

Fluorescence Rankings:

The RFU values from the Cleanospector represent the difference in fluorescence, or the amount of light that is reflected from a surface. Percent detergency demonstrates the amount of restoration to the original that has occurred after the cleaning test has been performed. A higher average percent detergency indicates that the cleaner has been effective and has restored the dirty substrate and cleaned it so that it now is much closer to how it originally was measured.

Data recorded from the readings can be calculated as percent detergency in the following equation to determine the cleaning efficacy of each formulation:

$$\% \text{ DET} = \frac{R(\text{cleaned}) - R(\text{soiled})}{R(\text{unsoiled}) - R(\text{soiled})} \times 100$$

The unsoiled RFU value was estimated to be 5.0 based on the measured RFU of carbon steel coupons from trial #0.

Visual Rankings:

- 1= 100% soil removed
- 2= 75% soil removed
- 3= 50% soil removed
- 4= 25% soil removed
- 5= 0% soil removed

Results:

Part Sample	% DET based on carbon steel	AVG % DET	Overall % DET
Carbon Steel Flags	97.10%	97.14%	96.02%
	96.77%		
	97.54%		
Carbon Steel Caps	94.57%	94.90%	
	94.79%		
	95.34%		

Cleanospector

Part Sample	Visual	AVG Visual	Overall Visual
Carbon Steel Flags	1.5	1.2	1.1
	1.2		
	1		
Carbon Steel Caps	1	1	
	1		

CLEANING LABORATORY EVALUATION SUMMARY

	1		
--	---	--	--

Visual

Summary:

Substrates:		Carbon Steel			
Contaminants:		Cutting/Tapping Fluids, Greases, Lubricating/Lapping Oils, Oil, Silicones			
Company Name:	Product Name:	Conc.:	Efficiency:	Effective:	Observations:
Dow Chemical Company	PnB Glycol Ether	98%	96.02	<input checked="" type="checkbox"/>	

Conclusion:

The additional time added to the heated immersion method resulted in increased efficacy of the PnB Glycol Ether. There was still a very small amount of soil left on only some of the flags threading. PnB Glycol Ether is a highly effective cleaner in removing the provided soil.