

CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 2006
DateRun: 02/14/2006
Experimenters: Jason Marshall
ClientType: Chemical Company
ProjectNumber: Project #2
Substrates: Gold
PartType: Coupon
Contaminants: Dirt, Fingerprints, Oil
Cleaning Methods: Immersion/Soak
Analytical Methods: Gravimetric
Purpose: To evaluate supplied products on fingerprint-light oil-dirt mix from gold coupons in heated cleaning.

Experimental Procedure: Two requested powdered products were made into solution by adding 3 grams of powder to 250 ml of tap water at 120 F. The supplied gold coupons were weighed to establish a base line weight. The coupons were then wiped with isopropyl alcohol and weighed again to determine if the coupons were free of any contamination. When the weight of the coupons did not vary after being wiped, the true baseline weights were recorded.

Fingerprints were then applied to the surface. Approximately 0.0005 grams of finger oil were applied to each coupon. In addition a oil-dirt mix also was applied. The oil-dirt mix consisted of 25 ml of Mobil Oil Corp Vactra Oil Light and 1.00 grams of dirt collected from a vacuum cleaner. The two components were mixed together and applied over the fingerprints using a hand held swab. Coupons were then weighed again to determine the total soil added. Three coupons were immersed in a 150 ml glass beaker filled with each solution at 120 F. Cleaning lasted for 5 minutes using stir-bar agitation. After cleaning coupons were immersed briefly (5 seconds) into a tap water rinse bath at 120 F, air dried using compressed air and then weighed to determine the amount of soil remaining. Final weights were recorded and efficiency of each cleaning solution was calculated.

Results: One of the two products removed nearly 100% of the oil-dirt-fingerprint mixture after immersion cleaning at 120 F. The other removed over 90%. The table lists the amount of soil added, the amount remaining and the efficiency for each coupon cleaned.

Cleaner	Initial wt	Final wt	% Removed
Alconox	0.1246	0.0005	99.60
	0.0798	0.0002	99.75
	0.0931	0.0019	97.96
Tergajet	0.0856	0.0085	90.07
	0.0909	0.0035	96.15
	0.0954	0.0110	88.47

Summary:

Substrates:		Gold			
Contaminants:		Dirt, Fingerprints, Oil			
Company Name:	Product Name:	Conc.:	Efficiency:	Effective:	Observations:
Alconox Inc	Alconox	1.2	99.10	<input checked="" type="checkbox"/>	
Alconox Inc	Tergajet	1.2	91.56	<input checked="" type="checkbox"/>	

Conclusion: The Alconox powder solution removed 99% of the oil-dirt-fingerprint mix and the Tergajet removed over 90% while heated to 120 F.