

# CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 2008  
 DateRun: 04/30/2008  
 Experimenters: Jason Marshall  
 ClientType: Machining Company  
 ProjectNumber: Project #1  
 Substrates: Aluminum  
 PartType: Coupon  
 Contaminants: Inks  
 Cleaning Methods: Manual Wipe  
 Analytical Methods: Visual

Purpose: To evaluate previously tested product at lower concentrations for cleaning the six inks.

Experimental Procedure: Coupons were coated with each of the six supplied inks. These included Dykem Stop Off, Markal Valve Action Paint marker, Nu-Mark marker, Sharpie permanent marker, Sakura Coatings Product Company Solid Marker and the Avery Marks-A-Lot permanent marker (black). Once dry, coupons were cleaned using a handheld swab that was immersed into the cleaning product. Cleaning lasted for up to 2 minutes. Following the cleaning, the coupons was wiped once to dry surface. Observations were made and recorded.

Three dilutions were evaluated: 40%, 20% and 10%. If the dilution required under one minute to be effective, then a lower concentration also was evaluated. If the dilution took longer than a minute and a half, a higher concentration was evaluated.

Results: The two most challenging inks for the diluted product were blue sharpie and the black Avery Marks-a-lot marker. The easiest to remove was the Nu Marker, which was cleaned at 10% in less than 20 seconds.

Contaminant	Dilution	Observations
Dykem	40%	40 seconds to clean
	20%	90 seconds
Markal	20%	20 seconds
	10%	40 seconds
Nu Mark	20%	15 seconds
	10%	15 seconds
Sharpie	20%	120 seconds - 90% removed
	40%	60 seconds - 95% removed
Solid Yellow	20%	90 seconds
	40%	90 seconds
Marks-a-lot	20%	120 seconds -95% removed
	40%	60 seconds - 95% removed

Summary:

<b>Substrates:</b>		Aluminum			
<b>Contaminants:</b>		Inks			
<b>Company Name:</b>	<b>Product Name:</b>	<b>Conc.:</b>	<b>Efficiency:</b>	<b>Effective:</b>	<b>Observations:</b>
Vertec BioSolvents	VertecBio Gold 3	20		<input checked="" type="checkbox"/>	

Conclusion: The Vertec Bio Gold 3 was found to be effective on the six contaminants when diluted with water. The 20% dilution may be the best choice for a universal concentration for all six inks.