

# CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 1997  
 DateRun: 12/09/1997  
 Experimenters: Jason Marshall  
 ClientType: Manufacturer of Security Systems  
 ProjectNumber: Project #1  
 Substrates: Steel  
 PartType: Part  
 Contaminants: Cutting/Tapping Fluids, Lubricating/Lapping Oils, Oil  
 Cleaning Methods: Immersion/Soak  
 Analytical Methods: Gravimetric  
 Purpose: Compare different aged bath cleaning capabilities

Experimental Procedure: The experiment was performed in the same manner as the previous trials by contaminating preweighed coupons with the Quaker oil, weighing, then cleaning, rinsing, drying and finally weighing again. The coupons were then cleaned using stir bar agitation in a beaker at 130 F for two minutes. Rinsing was done by immersing the parts in tap water at 120 F for thirty seconds in a beaker. Drying was conducted with an Original Disc Furnace portable heater, model # 1500IV, until the parts were completely dry. Four cleaning ages were tested: Zero month, one month, two months, three months old and three months new.  
 SUBSTRATE MATERIAL: 1020 Cold rolled steel  
 CONTAMINANT: Quaker C1A US oil

Results: The percent removal of the oil from the coupons were fairly consistent with the previous trials, the efficiency decreasing as the bath got older. See Table 1 for results.

Table 1 Percent Removal of Contaminants

Month	0	1	2	3old	3new
	99.9	91.4	96.5	93.9	84.2
	99.8	92.3	99.1	91.8	93.4
	100	86.5	91.9	84.9	75.7
Ave	99.9	90.5	96.5	90.2	84.4
Std Dev	0.1	3.12	3.65	4.71	8.85

The one month sample was the only exception to the trend. It had a lower efficiency than the two month sample. The decreased efficiency could be due to how well the cleaning solutions were mixed prior to use. In the previous trial, the efficiency of the 3 month sample was only 42% and it had been suggested that the solution needed to be shaken in order to get a uniform mixture.

The three month sample this time was shaken and had an efficiency of 90%, thus showing that mixing was needed to obtain accurate results. Inadequate mixing would result in an abnormal amount of oil present in the cleaning solution resulting in a lower than expected efficiency. In the next trial, all samples will be shaken for a set period of time to ensure consistent cleaning.

Summary:

<b>Substrates:</b>	Steel				
<b>Contaminants:</b>	Cutting/Tapping Fluids, Lubricating/Lapping Oils, Oil				
<b>Company Name:</b>	<b>Product Name:</b>	<b>Conc.:</b>	<b>Efficiency:</b>	<b>Effective:</b>	<b>Observations:</b>
Oakite Products	Inproclean 1300	3		<input checked="" type="checkbox"/>	

Conclusion: The cleaning efficiencies of the various bath ages were similar to previous test results with only one exception. The one month sample had a lower efficiency than the two month sample. Proper shaking of the cleaners prior to use may eliminate this discrepancy.