CLEANING LABORATORY EVALUATION SUMMARY

SCL #:	1999
DateRun:	08/26/1999
Experimenters:	Nicole Vayo
ClientType:	Lab
ProjectNumber:	Project #1
Substrates:	Aluminum, Brass, Copper, Nickel, Stainless Steel
PartType:	Coupon
Contaminants:	Greases, Lubricating/Lapping Oils, Oil
Cleaning Methods:	Immersion/Soak
Analytical Methods:	Gravimetric
Purpose:	Laboratory evaluations of alternative cleaning products
Experimental Procedure:	Basic cleaning performance testing was conducted using ASTM G122 as the bases for cleaning. Laboratory evaluation. Contaminant: Grease, CAS: 64742-47-8 Oil, CAS: 64741-89-5 Lubricant, CAS: 64742-47-8, 9003-29-6
Results:	Accu clean removed blue stain from brass coupon

Summary:

Substrates:	Aluminum, Brass, Copper, Nickel, Stainless Steel				
Contaminants:	Greases, Lubricating/Lapping Oils, Oil				
Company Name:	**Product Name:**	**Conc.:**	**Efficiency:**	**Effective:**	**Observations:**
Watson Technical Associates	Watson Formula 9000	10	89.97	☑	grease
Watson Technical Associates	Watson Formula 9000	10	79.50	☐	oil
Watson Technical Associates	Watson Formula 9000	10	92.50	☑	lubricant
ITW Fluid Products Group	AccuClean	10	97.50	☑	grease
ITW Fluid Products Group	AccuClean	10	78.80	☐	oil
ITW Fluid Products Group	AccuClean	10	95.60	☑	lubricant

Conclusion: