CLEANING LABORATORY EVALUATION SUMMARY

SCL #:	1999
DateRun:	09/20/1999
Experimenters:	Nicole Vayo
ClientType:	Lab
ProjectNumber:	Project #1
Substrates:	Aluminum, Brass, Copper, Nickel
PartType:	Coupon
Contaminants:	Coatings, Inks, Oil
Cleaning Methods:	Immersion/Soak
Analytical Methods:	Gravimetric
Purpose:	Laboratory evaluations of alternative cleaning products
Experimental Procedure:	Basic cleaning performance testing was conducted using ASTM G122 as the bases for cleaning. L aboratory evaluation. Contaminant: Ink, CAS: 67-63-0, 108-88-3, 9004-70-0, 109-60-4, 141-78-6, 64-17-5 Oil, CAS: 64741-89-5 Coating, CAS: 64742-47-8, 64742-52-5
Results:	
Summary:	

Substrates:	Aluminum, Brass, Copper, Nickel
Contaminants:	Coatings, Inks, Oil

Company Name:	Product Name:	Conc.:	Efficiency:	Effective:	Observations:
Permatex Industrial Corporation	Natural Blue	5	79.70	☐	coating
Permatex Industrial Corporation	Natural Blue	5	0.26	☐	ink
Permatex Industrial Corporation	Natural Blue	5	93.50	☑	oil
Oakite Products	Okemclean	5	55.30	☐	coating
Oakite Products	Okemclean	5	-0.86	☐	ink
Oakite Products	Okemclean	5	94.70	☑	oil
Texo Corporation	Texolite 1734 XL	5	86.50	☑	coating
Texo Corporation	Texolite 1734 XL	5	95.00	☑	oil

Conclusion: