CLEANING LABORATORY EVALUATION SUMMARY

SCL #:	1999
DateRun:	10/13/1999
Experimenters:	Nicole Vayo
ClientType:	Lab
ProjectNumber:	Project #1
Substrates:	Aluminum, Brass, Stainless Steel
PartType:	Coupon
Contaminants:	Adhesive, Coatings, Fluxes, Greases, Inks
Cleaning Methods:	Immersion/Soak
Analytical Methods:	Gravimetric
Purpose:	Laboratory evaluations of alternative cleaning products
Experimental Procedure:	Basic cleaning performance testing was conducted using ASTM G122 as the bases for cleaning. Laboratory evaluation. Contaminant: Adhesive, CAS: 9010-98-4, 95997-13-9, 68083-03-4, 108-88-3 Flux, RMA Coating, CAS: 64742-47-8, 64742-52-5 Grease, CAS: 64742-47-8 Ink, CAS: 67-63-0, 108-88-3, 9004-70-0, 109-60-4, 141-78-6, 64-17-5
Results:	
Summary:	

Substrates:	Aluminum, Brass, Stainless Steel				
Contaminants:	Adhesive, Coatings, Fluxes, Greases, Inks				
Company Name:	**Product Name:**	**Conc.:**	**Efficiency:**	**Effective:**	**Observations:**
Emkay Chemical Company	Safety Wash CRC	5	88.20	☑	flux
Emkay Chemical Company	Safety Wash CRC	5	14.30	☐	adhesive
Emkay Chemical Company	Safety Wash CRC	5	100.20	☑	grease
Emkay Chemical Company	Safety Wash CRC	5	3.30	☐	ink
Emkay Chemical Company	Safety Wash CRC	5	94.20	☑	coating
Church & Dwight Co Inc.	Armakleen E 2001	5	94.80	☑	flux
Brulin Corporation	Formula 815 GD	5	51.20	☐	flux

Conclusion: