

# CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 2001

DateRun: 03/31/2001

Experimenters: John Brunelle

ClientType: Lab

ProjectNumber: Project #1

Substrates: Aluminum, Brass, Copper, Glass/Quartz, Nickel, Stainless Steel

PartType: Coupon

Contaminants: Coatings, Greases, Inks, Oil

Cleaning Methods: Immersion/Soak

Analytical Methods: Gravimetric

Purpose: Laboratory evaluations of alternative cleaning products

Experimental Procedure: Basic cleaning performance testing was conducted using ASTM G122 as the bases for cleaning.  
Laboratory evaluation.  
Contaminant: Ink, CAS: 67-63-0, 108-88-3, 9004-70-0, 109-60-4, 141-78-6, 64-17-5  
Grease, CAS: 64742-47-8  
Oil, CAS: 64741-89-5, 8052-42-4  
Coating, CAS: 64742-47-8, 64742-52-5

## Results:

### Summary:

<b>Substrates:</b>	Aluminum, Brass, Copper, Glass/Quartz, Nickel, Stainless Steel				
<b>Contaminants:</b>	Coatings, Greases, Inks, Oil				
<b>Company Name:</b>	<b>Product Name:</b>	<b>Conc.:</b>	<b>Efficiency:</b>	<b>Effective:</b>	<b>Observations:</b>
Pride International Inc	Citrisolv Plus	10	-30.40	<input type="checkbox"/>	ink
Pride International Inc	Citrisolv Plus	10	72.40	<input type="checkbox"/>	coating
Kyzen Corporation	Ionox FCR (For Comparison Only)	100	98.16	<input checked="" type="checkbox"/>	grease
Kyzen Corporation	Ionox FCR (For Comparison Only)	100	94.20	<input checked="" type="checkbox"/>	oil
Kyzen Corporation	Ionox FCR (For Comparison Only)	100	53.73	<input type="checkbox"/>	coating
Finger Lakes Chemical	FLSC-12 Resineater Sample	100	87.57	<input checked="" type="checkbox"/>	ink
Finger Lakes Chemical	FLSC-12 Resineater Sample	100	87.23	<input checked="" type="checkbox"/>	grease
Finger Lakes Chemical	FLSC-12 Resineater Sample	100	85.73	<input checked="" type="checkbox"/>	oil
EcoLink	Safe Strip	100	71.61	<input type="checkbox"/>	ink
EcoLink	Safe Strip	100	70.82	<input type="checkbox"/>	grease

### Conclusion: