CLEANING LABORATORY EVALUATION SUMMARY

SCL #:	2000
DateRun:	06/06/2000
Experimenters:	Nicole Vayo
ClientType:	Lab
ProjectNumber:	Project #1
Substrates:	Aluminum, Brass, Copper, Nickel, Stainless Steel
PartType:	Coupon
Contaminants:	Coatings, Greases, Lubricating/Lapping Oils, Oil
Cleaning Methods:	Immersion/Soak
Analytical Methods:	Gravimetric
Purpose:	Laboratory evaluations of alternative cleaning products
Experimental Procedure:	Basic cleaning performance testing was conducted using ASTM G122 as the bases for cleaning. Laboratory evaluation. Contaminant: Oil, Citgo NC 400, CAS: 8052-42-4, 64742-57-0, 64742-62-7 Lubricant, CAS: 8052-42-4, 64742-57-0, 64742-62-7 Grease, CAS: 64742-47-8 Coating, CAS: 64742-47-8, 64742-52-5
Results:	
Summary:	

Substrates:	Aluminum, Brass, Copper, Nickel, Stainless Steel				
Contaminants:	Coatings, Greases, Lubricating/Lapping Oils, Oil				
Company Name:	**Product Name:**	**Conc.:**	**Efficiency:**	**Effective:**	**Observations:**
Warren Chemical Company	Sea Wash 8 No Force	5	99.89	☑	oil
Warren Chemical Company	Sea Wash 8 No Force	5	98.89	☑	grease
Warren Chemical Company	Sea Wash 8 No Force	5	99.82	☑	lubricant
Warren Chemical Company	Sea Wash 8 No Force	5	99.39	☑	coating

Conclusion: