CLEANING LABORATORY EVALUATION SUMMARY

SCL #:	2001
DateRun:	06/26/2001
Experimenters:	Ravi Krishnappa
ClientType:	Lab
ProjectNumber:	Project #1
Substrates:	Aluminum, Steel
PartType:	Coupon
Contaminants:	Adhesive, Coatings, Inks
Cleaning Methods:	Immersion/Soak
Analytical Methods:	Gravimetric
Purpose:	Laboratory evaluations of alternative cleaning products
Experimental Procedure:	Basic cleaning performance testing was conducted using ASTM G122 as the bases for cleaning. Laboratory evaluation. Contaminant: Adhesive, Ideal Tape AC059, CAS: 108-88-3 Coating, Heraeus Covercoat L406, CAS: 85-68-7, 108-67-8 Ink, Tough Tex
Results:	
Summary:	

Substrates:	Aluminum, Steel				
Contaminants:	Adhesive, Coatings, Inks				
Company Name:	**Product Name:**	**Conc.:**	**Efficiency:**	**Effective:**	**Observations:**
Warren Chemical Company	Sea Wash 8	5	35.80	☐	coating
Warren Chemical Company	Sea Wash 8	5	1.18	☐	ink
CRC Industries	Complex Blue	5	36.05	☐	coating
CRC Industries	Complex Blue	5	0.72	☐	ink
Bio Chem Systems	Bio T 200 A	100	45.32	☐	adhesive
Bio Chem Systems	Bio T 200 A	100	39.30	☐	ink

Conclusion: