CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 2001

DateRun: 07/04/2001

Experimenters: Ravi Krishnappa

ClientType: Lab

ProjectNumber: Project #1

Substrates: Stainless Steel

PartType: Coupon

Contaminants: Adhesive

Cleaning Methods: Immersion/Soak

Analytical Methods: Gravimetric

Purpose: Laboratory evaluations of alternative cleaning products

Experimental Procedure: Basic cleaning performance testing was conducted using ASTM G122 as the bases for cleaning.
Laboratory evaluation.
Contaminant: Adhesive Ashland Aroset 8034, CAS: 141-78-6, 67-63-0, 108-88-3

Results:

Summary:

Substrates:	Stainless Steel				
Contaminants:	Adhesive				
Company Name:	**Product Name:**	**Conc.:**	**Efficiency:**	**Effective:**	**Observations:**
Savogran Company	SI #4 Coating Remover	100	2.66	☐	
Buckeye International	Shopmaster	20	5.41	☐	
Dysol	DS 104 Wipe Solvent	100	8.20	☐	
Bio Chem Systems	Bio T 200 A	100	0.57	☐	
Bio Chem Systems	Bio T Max	100	-4.92	☐	
Inland Technologies Inc	EP 921	100	-8.70	☐	
Safe Science Inc	Safe Science Engine Degreaser (Industrial)	100	7.40	☐	
Transene Company, Inc.	D Greeze 500 LO	100	4.20	☐	
Twin Rivers Technologies	Methyl Ester 1618	100	-85.60	☐	

Conclusion: