

# CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 2001  
 DateRun: 07/12/2001  
 Experimenters: Ravi Krishnappa  
 ClientType: Lab  
 ProjectNumber: Project #1  
 Substrates: Stainless Steel  
 PartType: Coupon  
 Contaminants: Oil  
 Cleaning Methods: Ultrasonics  
 Analytical Methods: Gravimetric  
 Purpose: Laboratory evaluations of alternative cleaning products  
 Experimental Procedure: Basic cleaning performance testing was conducted using ASTM G122 as the bases for cleaning.  
 Laboratory evaluation.  
 Contaminant: Oil, Hydraulic, CAS: 64742-65-0

## Results:

### Summary:

|                               |                           |               |                    |                                     |                      |
|-------------------------------|---------------------------|---------------|--------------------|-------------------------------------|----------------------|
| <b>Substrates:</b>            | Stainless Steel           |               |                    |                                     |                      |
| <b>Contaminants:</b>          | Oil                       |               |                    |                                     |                      |
| <b>Company Name:</b>          | <b>Product Name:</b>      | <b>Conc.:</b> | <b>Efficiency:</b> | <b>Effective:</b>                   | <b>Observations:</b> |
| Heatbath Corporation          | Uni Kleen 10              | 4             | 97.60              | <input checked="" type="checkbox"/> |                      |
| MacDermid Industrial Products | New Dimensions LF Supreme | 4             | 94.90              | <input checked="" type="checkbox"/> |                      |
| International Bio System      | Bio Z                     | 10            | 92.70              | <input checked="" type="checkbox"/> |                      |

### Conclusion: