CLEANING LABORATORY EVALUATION SUMMARY

SCL #:	2001
DateRun:	07/16/2001
Experimenters:	Ravi Krishnappa
ClientType:	Lab
ProjectNumber:	Project #1
Substrates:	Stainless Steel
PartType:	Coupon
Contaminants:	Adhesive, Greases, Oil
Cleaning Methods:	Immersion/Soak
Analytical Methods:	Gravimetric
Purpose:	Laboratory evaluations of alternative cleaning products
Experimental Procedure:	Basic cleaning performance testing was conducted using ASTM G122 as the bases for cleaning. Laboratory evaluation. Contaminant: Adhesive Ashland Aroset 8034, CAS: 141-78-6, 67-63-0, 108-88-3 Oil, Citgo Cutting Oil NC120, CAS: 64741-89-5, 64742-65-0 Grease, KSL 111, CAS: 64742-47-8
Results:	
Summary:	

Substrates:	Stainless Steel				
Contaminants:	Adhesive, Greases, Oil				
Company Name:	**Product Name:**	**Conc.:**	**Efficiency:**	**Effective:**	**Observations:**
Loctite Corporation	7360	100	0.06	☐	adhesive
Innovative Organics Inc	Amberclean SC 11	5	86.30	☑	grease
Heatbath Corporation	MultiKleen LX 1573	5	98.30	☑	oil

Conclusion: