CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 2001

DateRun: 08/22/2001

Experimenters: Ravi Krishnappa

ClientType: Lab

ProjectNumber: Project #1

Substrates: Aluminum

PartType: Coupon

Contaminants: Coatings

Cleaning Methods: Immersion/Soak

Analytical Methods: Gravimetric

Purpose: Laboratory evaluations of alternative cleaning products

Experimental Procedure: Basic cleaning performance testing was conducted using ASTM G122 as the bases for cleaning.
Laboratory evaluation.
Contaminant: Coating, Ferrocote 5815, CAS: 64742-47-8, 64742-52-5

Results:

Summary:

Substrates:	Aluminum				
Contaminants:	Coatings				
Company Name:	**Product Name:**	**Conc.:**	**Efficiency:**	**Effective:**	**Observations:**
Loctite Corporation	7360	100	61.40	☐	
Gemtek Products	SC 1000 Aqueous Cleaner Concentrate	25	57.90	☐	
International Products Corporation	Micro 90 Conc.	5	44.30	☐	
Savogran Company	HD-34 Cleaner Degreaser	50	81.00	☑	
Chrisal USA Inc	Super CMF 240	15	69.60	☐	

Conclusion: