

# CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 2001  
 DateRun: 08/23/2001  
 Experimenters: Ravi Krishnappa  
 ClientType: Lab  
 ProjectNumber: Project #1  
 Substrates: Aluminum  
 PartType: Coupon  
 Contaminants: Coatings  
 Cleaning Methods: Immersion/Soak  
 Analytical Methods: Gravimetric  
 Purpose: Laboratory evaluations of alternative cleaning products  
 Experimental Procedure: Basic cleaning performance testing was conducted using ASTM G122 as the bases for cleaning.  
 Laboratory evaluation.  
 Contaminant: Coating, Ferrocote 5815, CAS: 64742-47-8, 64742-52-5

## Results:

### Summary:

<b>Substrates:</b>	Aluminum				
<b>Contaminants:</b>	Coatings				
<b>Company Name:</b>	<b>Product Name:</b>	<b>Conc.:</b>	<b>Efficiency:</b>	<b>Effective:</b>	<b>Observations:</b>
Loctite Corporation	7360	100	61.40	<input type="checkbox"/>	
Gemtek Products	SC 1000 Aqueous Cleaner Concentrate	25	57.90	<input type="checkbox"/>	
International Products Corporation	Micro 90 Conc.	5	44.30	<input type="checkbox"/>	
Savogran Company	HD-34 Cleaner Degreaser	50	81.00	<input checked="" type="checkbox"/>	
Chrisal USA Inc	Super CMF 240	15	69.60	<input type="checkbox"/>	

### Conclusion: