CLEANING LABORATORY EVALUATION SUMMARY

SCL #:	2001
DateRun:	08/29/2001
Experimenters:	Ravi Krishnappa
ClientType:	Lab
ProjectNumber:	Project #1
Substrates:	Aluminum
PartType:	Coupon
Contaminants:	Paints
Cleaning Methods:	Immersion/Soak
Analytical Methods:	Gravimetric
Purpose:	Laboratory evaluations of alternative cleaning products
Experimental Procedure:	Basic cleaning performance testing was conducted using ASTM G122 as the bases for cleaning. Laboratory evaluation. Contaminant: Paint, Painter Touch Blue, CAS: 67-64-0, 1330-20-07
Results:	
Summary:	

Substrates:	Aluminum				
Contaminants:	Paints				
Company Name:	**Product Name:**	**Conc.:**	**Efficiency:**	**Effective:**	**Observations:**
Savogran Company	SI #4 Coating Remover	100	-4.65	☐	
Gemtek Products	SC Supersolve Safety Solvent	30	5.62	☐	
Twin Rivers Technologies	Methyl Ester 1618	100	87.80	☑	
Invista S.a.r.l	Flexisolv DBE 4 ester	100	89.30	☑	

Conclusion: