CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 2001

DateRun: 10/09/2001

Experimenters: Ravi Krishnappa

ClientType: Lab

ProjectNumber: Project #1

Substrates: Stainless Steel

PartType: Coupon

Contaminants: Adhesive

Cleaning Methods: Ultrasonics

Analytical Methods: Gravimetric

Purpose: Laboratory evaluations of alternative cleaning products

Experimental Procedure: Basic cleaning performance testing was conducted using ASTM G122 as the bases for cleaning.
Laboratory evaluation.
Contaminant: Adhesive Ashland Acrylic Sealant 5504, CAS: 108-88-3, 141-78-6, 142-82-5, 67-63-0

Results:

Summary:

Substrates:	Stainless Steel				
Contaminants:	Adhesive				
Company Name:	**Product Name:**	**Conc.:**	**Efficiency:**	**Effective:**	**Observations:**
Invista S.a.r.l	Flexisolv DBE 4 ester	100	99.30	☑	
Ensolve Biosystems Inc	Grease Feast Plus	5	6.60	☐	
Bio Chem Systems	Bio T Max	100	48.20	☐	
Bio Chem Systems	Bio T 300 B	5	9.42	☐	
Warren Chemical Company	Sea Wash 8	5	9.63	☐	

Conclusion: