CLEANING LABORATORY EVALUATION SUMMARY

SCL #:	2001
DateRun:	11/07/2001
Experimenters:	Ravi Krishnappa
ClientType:	Lab
ProjectNumber:	Project #1
Substrates:	Stainless Steel
PartType:	Coupon
Contaminants:	Lubricating/Lapping Oils
Cleaning Methods:	Immersion/Soak
Analytical Methods:	Gravimetric
Purpose:	Laboratory evaluations of alternative cleaning products
Experimental Procedure:	Basic cleaning performance testing was conducted using ASTM G122 as the bases for cleaning. Laboratory evaluation. Contaminant: Lubricant, Lubri Temp Anti Seize
Results:	
Summary:	

Substrates:	Stainless Steel				
Contaminants:	Lubricating/Lapping Oils				
Company Name:	**Product Name:**	**Conc.:**	**Efficiency:**	**Effective:**	**Observations:**
Brulin Corporation	Compliance	10	-27.90	☐	
AW Chesterton	278 Super Solv	10	14.50	☐	
US Polychem Corporation	87 RB	100	93.70	☑	
Bio Chem Systems	Bio T Max	100	88.60	☑	
Transene Company, Inc.	D Greeze 500 LO	100	91.00	☑	
Warren Chemical Company	Sea Wash 8	5	-40.60	☐	
Ensolve Biosystems Inc	Grease Feast Plus	5	4.90	☐	

Conclusion: